

TL 5-483-2023

Issue No.: 2

Effective from: 05.09.2025

Uncontrolled printing

Wall covering MODUL

APPLICATION

Heterogeneous PVC wall covering MODUL is used for gluing to the walls of interior spaces in the area of residential, commercial construction and light industry outside protected escape routes.

Description	Standard	Value
Heterogeneous PVC wall covering in rolls		
Total thickness *	EN ISO 24346	1.15 mm
Width *	EN ISO 24341	2000 mm
Total area weight *	EN ISO 23997	1900 g/m ²
Dimensional stability	EN ISO 23999	≤ 0.4 %
Classification according to EN 15102+A1:2012	Standard	Value
Reaction to fire	EN 13501-1	B-s2, d0
Release of formaldehyde	EN 12149	compliant
Release of heavy metals and specific elements	EN 12149	compliant
Release of vinylchloride monomer (VCM)	EN 12149	compliant
Technical parameters	Standard	Value
Stain resistance and chemical resistance	EN ISO 26987	compliant
Colour fastness to artificial light	EN ISO 105-B02 method 3	min. degree 6
Environment, safety	Standard	Value
Impact on the environment	ISO 14025	Environmental statement on the product (EPD)
Bacterial resistance	EN ISO 846 method C	compliant
Antibacterial activity of PUR varnish	ISO 22196	R ≥ 3
VOC	EN 16516	Complies with Decree No. 6/2003

* indicative value

PACKAGING

Dimension [mm]	Quantity per roll	
	[m]	[m ²]
1.15 x 2000	18	36

WALL COVER INSTALLATION

- The detailed procedure for the application of the MODUL wall covering is given in the PN 5427/2024 application regulation, available on the manufacturer's website www.fatrafloor.com.
- The substrate for laying must be flat, smooth, free of cracks and dust, sufficiently strong, clean and dry. Irregularities, greasy stains and others must be removed. Oil-painted walls must be sanded.
- Before laying, it is necessary to develop the wall covering and stabilize the surface and size (above + 18 °C, 48 hours).
- The serial numbers of the rolls must follow one after the other during installation to avoid differences in shade.
- The individual strips are welded with a Novoplast welding line or the cold welding method.
- It is not recommended to combine different production batches.

INSTRUCTIONS, TREATMENT, MAINTENANCE

- Store the wall covering at a temperature of +5 °C to +35 °C in a dry and dust-free interior min.1 m from a heat source, protect from direct sunlight and artificial lighting with a high UV component. The wall covering is intended for the interior.
- Operating conditions of the wall covering: air temperature +10 °C to +35 °C, relative air humidity (50 ± 10)%.
- Information on maintenance, care and cleaning of the MODUL wall covering is given in the PN 5427/2024 application regulation, available on the manufacturer's website www.fatrafloor.com.

WARRANTIES

The conditions for providing an extended warranty for 15 years are listed on the website www.fatra.cz.

